

EP 0 590 007

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>5</sup> : C08J 7/18 // C08J 7/18 C08L 27/18, B01D 69/12 B05D 7/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 93/00394 (43) International Publication Date: 7 January 1993 (07.01.93)</p>
<p>(21) International Application Number: PCT/GB92/01111 (22) International Filing Date: 19 June 1992 (19.06.92) (30) Priority data: 9113350.4 20 June 1991 (20.06.91) GB (71)(72) Applicant and Inventor: THOMAS, Thomas, Ronald [GB/GB]; Rowan House, Culbo Road, Culbokie, Ding- wall, Ross-Shire IV7 8JU (GB). (74) Agent: NEVILLE, Peter, Warwick; Patents Department, British Technology Group Ltd., 101 Newington Cause- way, London SE1 6BU (GB).</p>	<p>(81) Designated States: AU, CA, FI, JP, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LU, MC, NL, SE).  Published <i>With international search report.</i></p>	
<p>(54) Title: APPLYING A FLUOROPOLYMER FILM TO A BODY</p> <p>(57) Abstract</p> <p>A thin fluoropolymer film is covalently bonded to a microporous ptfe film to make a bilayer for separation, filtration or reverse osmosis, by exposing the microporous film to perfluorocyclohexane under plasma.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CZ	Czechoslovakia	LU	Luxembourg	TC	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

- 1 -

APPLYING A FLUOROPOLYMER FILM TO A BODY

This invention relates to applying a fluoropolymer film to a body, especially to porous and microporous films of fluoropolymers, and extends to coated bodies and two layer films

5 Microporous films and membranes from polymers are well known, and asymmetric forms find wide application in filtration and separation. Their manufacture is typically undertaken by a variety of casting processes and other relatively straightforward techniques allowable by the physical and chemical nature of the polymer. Polymers amenable to such straightforward techniques however are thermally, chemically and sometimes physically inferior to the more stable fluoropolymers, e.g. polytetrafluoroethylene (ptfe). Fluoropolymers are selected for  
10 their inertness and chemical resistance, and these very properties make it difficult to bond layers of fluoropolymers together. The techniques used for processing ptfe owe more to powder metallurgy than plastics as the material is not a true thermoplastic. The manufacture of such components most usually  
15 involves a compression moulding stage and a heat treatment or sintering stage.

PCT Publication WO 90/13593 discloses a mechanical bonding method for porous ptfe layers which are impregnated with perfluoro ion exchange polymer, and further refers to numerous  
25 earlier patents in the field. Such a mechanical bond may not be adequate for all applications. Japanese Laid-Open (Kokai) 62-204826 discloses coating a porous ptfe membrane in a plasma vessel by introducing gaseous tetrakis(trifluoromethyl)dithioethane, which forms a polymer in  
30 the form of a thin film on the membrane. This introduces sulphur into the product as well as  $-CF_3$  groups at the surface, which is unnecessarily hydrophobic for some applications.

- 2 -

These publications do not teach any way of making a well bonded bilayer of pure fluoropolymer. Such a bilayer could find application in filtration, separation or reverse osmosis.

It would thus be desirable to solve the problem of formation of a very thin continuous layer of fluoropolymer strongly bonded to the surface of a microporous fluoropolymer substrate.

According to the present invention, a method of applying a fluoropolymer film to a body comprises exposing the body to fragments exclusively of the formula  $-C_nF_{2n}-$ , under conditions whereby the fragments combine on the surface of the body to form an adherent fluoropolymer layer. Also according to the invention, a method of applying a fluoropolymer film to a body comprises exposing the body to a supply of saturated molecules of the formula  $C_nF_{2n}$ , causing scission of the molecules, and allowing the fragments to combine on the surface of the body to form an adherent fluoropolymer layer. The body may be carbonaceous polymer e.g. a fluoropolymer such as ptfe, optionally itself a film, which may be porous or microporous, in which case the layer will be covalently bonded thereto. The molecules may be cyclo-perfluoroalkanes e.g.  $C_nF_{2n}$  where  $n = 4 - 8$ , preferably 6. The reason for preferring perfluorocycloalkane is that it can undergo scission affording only multiple  $CF_2$  units, in particular no  $CF_3$  fragments at all. This cannot occur with non-cyclic saturated fluoroalkanes. This allows the product to be as close to ptfe, i.e.  $CF_2$  linkages, as possible, avoiding multiple  $CF_3$  fragments, which are more hydrophobic than  $CF_2$ . Of the perfluorocycloalkanes, the butane tends to instability, the pentane is possible, while the heptane and octane are becoming exotic for no real gain. The hexane is therefore the most preferred, from cost, stability, availability and volatility points of view.

- 3 -

The body may be etched with a noble gas plasma e.g. argon at say 10 - 30W, for the purpose of cleaning, before the film is applied. Thereafter, the body may be subjected to a somewhat gentle plasma irradiation, preferably <5W, e.g. 0.1-50W, in a chamber which may be evacuated to 0.01 to 5 torr, such as 0.2 to 0.3 torr, of fluorocarbon. Expressed in terms of unit area-to-be-coated of the body, preferred plasma powers are <100W/m<sup>2</sup>, e.g. 2-1000W/m<sup>2</sup>. Lower powers lessen undesirable cross-linking.

- 10 As a new product in its own right, the invention provides a carbonaceous polymer (e.g. ptfе) body covalently bonded to a fluoropolymer film. Likewise as a new product, the invention provides a two layer fluoropolymer film containing no atoms other than of carbon and halogen and which cannot be delaminated by hand.

15 A specific embodiment of the invention will now be described by way of example, for producing a continuous film of plasma polymer upon a microporous polymeric substrate.

- Microporous ptfе film manufactured by the Mupor<sup>TM</sup> procedure, 20 European Patent 247771, is the substrate to be coated. A 0.06m<sup>2</sup> sample of it is placed in an enclosure which is then evacuated to low pressures, about 0.05 torr, to remove air and moisture. Plasma of power 5W is then generated in the enclosure via say high voltage, 3000 to 40000 volts or by a high frequency 25 generator, say 10MHz or 13.56MHz. Perfluorocyclohexane at 0.2 torr is introduced into the cavity at 0.2ml/min.

- Under these conditions very reactive species are produced which in turn react with the surface of the article, which reactive sites can then in turn react with monomeric species 30 introduced into the enclosure. The experimental conditions required will vary from one system to another and the techniques and durations employed similarly can be varied to suit individual requirements, e.g. 'etching' where surfaces can be cleaned by the gradual erosion of the surface by reactive species, plasma 35 polymerisation and plasma initiated 'grafting'. The cyclo-C<sub>6</sub>F<sub>12</sub>

- 4 -

- is subjected to a sufficiently high electron voltage to generate perfluoro fragments, e.g.  $\text{CF}_2$ ,  $\text{C}_2\text{F}_4$ ,  $\text{C}_3\text{F}_6$ . These species then react to form a layer of plasma polymer across, and covalently bonded to, the surface and, in so doing, fill the pore entrances, eventually building into a controlled continuous thin film, the process being terminated when the required properties have been attained. Coating a ptfe film having 4-micron pores under these conditions for 10 minutes yielded a coating several microns thick completely sealing the pores. For typical smaller-pore films, a useful product may be attained in say 2 minutes.

- It will be noted that the process occurs in the gas phase under very mild conditions. The plasma generated within the cyclohexane atmosphere creates active fragments (radicals etc) based on  $\text{CF}_2$  units which polymerise and attach to the surface of the membrane in situ, which itself remains at a temperature of around 300K.

- Clearly careful control will ensure the thinnest continuous layer to maximise the aqueous flow rates during e.g. reverse osmosis separations of saline or brackish water.
- Such materials have great utility in the field of filtration and separation allowing for the first time a membrane filter with the chemical, biological and thermal advantages of ptfe but with advantageous flux rates associated with the very thin active layer.
- Other so-called anisotropic ptfe filters have poor bond strength between the substrate and the active layer. This technique not only allows great control over the film properties but ensures the strongest possible adhesion to the substrate.
- The process is both rapid and cost effective and additionally has wide applicability in the separative field. For example composite materials can be manufactured with great savings, e.g. in those situations where the active layers are very expensive a lower cost substrate can be used thus minimising the quantity of the active layer.

- 5 -

A further application embodies dissimilar monomeric species attached to both sides of the substrate, and additionally the technique is equally effective on other geometries, e.g. tubular and granular forms of the substrate ptf. This now allows  
5 separations of materials in areas of chromatography normally restricted to silica-based phases.

- 6 -

CLAIMS

1. A method of applying a fluoropolymer film to a body, comprising exposing the body to fragments exclusively of the  
5 formula  $-C_nF_{2n}-$ , under conditions whereby the fragments combine on the surface of the body to form an adherent fluoropolymer layer.
2. A method of applying a fluoropolymer film to a body of carbonaceous polymer, comprising exposing the body to fragments  
10 exclusively of the formula  $-C_nF_{2n}-$ , under conditions whereby the fragments combine on the surface of the body to form a fluoropolymer layer covalently bonded to the body.
3. A method of applying a fluoropolymer film to a body, comprising exposing the body to a supply of saturated molecules  
15 of the formula  $C_nF_{2n}$ , causing scission of the molecules, and allowing the fragments to combine on the surface of the body to form an adherent fluoropolymer layer.
4. A method of applying a fluoropolymer film to a body of carbonaceous polymer, comprising exposing the body to a supply of  
20 saturated molecules of the formula  $C_nF_{2n}$ , causing scission of the molecules, and allowing the fragments to combine on the surface of the body to form a fluoropolymer layer covalently bonded to the body.
5. A method according to Claim 2 or 4, wherein the carbonaceous  
25 polymer is a fluoropolymer.
6. A method according to any preceding claim, wherein the body is itself a film.
7. A method according to Claim 6, wherein the body is a porous or microporous film.
- 30 8. A method according to any of Claims 3 to 7, wherein the molecules are of cycloperfluoroalkane.



- 7 -

8. A method according to Claim 8, wherein the molecules are of cyclo-C<sub>n</sub>F<sub>2n</sub> where n = 4,5,7 or 8.
10. A method according to Claim 8, wherein the molecules are of cycloperfluorohexane.
- 5 11. A method according to any preceding claim, wherein the body is etched before the application of said film thereto.
12. A method according to any preceding claim, wherein the body is subjected to plasma irradiation during its exposure.
13. A method according to Claim 12, wherein the plasma power is less than 5W.
- 10 14. A method according to Claim 12, wherein the plasma power is from 0.1 to 50W.
15. A method according to any preceding claim, performed in a chamber evacuated to 0.01 to 5 torr.
- 15 16. A carbonaceous polymer body covalently bonded to a fluoropolymer film.
17. A body according to Claim 16, wherein the body is of ptfe.
18. A two layer fluoropolymer film containing no atoms other than of carbon and halogen and which cannot be delaminated by
- 20 hand.